



Customer : Prepack Thailand Co.,Ltd.
Testing Standard : ASTM D3985
Testing Device : MOCON OX-TRAN® 2/22(L)
Test range of Film : 0.005 to 2000 cc/(m²-day)
Test range of Package : 0.00003 to 1.0 cc/(pkg-day)
Sample Description : PE Film
Sample Receiving Date : 25/10/2565
Testing Period : 31/10/2565 - 02/11/2565

Testing Results : (Oxygen Transmission Rate, OTR)

Conditions : Temperature : 23 °C
: Relative Humidity
- Testing Gas RH : 0 %RH
- Carrier Gas RH : 0 %RH
: Testing Area : 50 cm²

No.	Sample	Oxygen Transmission Rate, OTR (cc/(m ² -day))
1	MDO / LLDPE (Barrier) CD	3.672

1. Reports relate only to the samples tested and are based on a single analysis.

2. The report shall not be changed, added, or modified without the prior written consent of Plastics Institute of Thailand.



Sample




Fig. 2 MDO / LLDPE (Barrier) CD

(Rattanabhorn Angkunlertbaramee)

Assistant Analyst

Tester

(Nattula Wongta)

Assistant Manager of Testing & Certification Center

Examiner

1. Reports relate only to the samples tested and are issued in academic analysis.
2. The report shall not be changed, added, or modified without the prior written consent of Plastics Institute of Thailand.